

PA 1098286



THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE

United States Patent and Trademark Office

November 26, 2003

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A FILING DATE UNDER 35 USC 111.

APPLICATION NUMBER: 60/498,155

FILING DATE: August 27, 2003

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)



By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS

P. SWAIN

Certifying Officer


BEST AVAILABLE COPY

PROVISIONAL APPLICATION FOR PATENT COVER SHEET

This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

Express Mail Label No.

ER132926898US

INVENTOR(S)						
Given Name (first and middle [if any])	Family Name or Surname	Residence (City and either State or Foreign Country)				
Reinhard Hans-Friedrich Michael	Kuhl Enderle Witt	Ludwigshafen, Netherlands Frankfurt, Germany Rotorua, New Zealand				
<input type="checkbox"/> Additional inventors are being named on the _____ separately numbered sheets attached hereto						
TITLE OF THE INVENTION (500 characters max)						
PROCESS FOR GRANULATING POWDERS OF THERMOPLASTIC POLYMERS						
Direct all correspondence to:		CORRESPONDENCE ADDRESS				
<input checked="" type="checkbox"/> Customer Number		34872				
OR		Type Customer Number here		34872		
<input type="checkbox"/> Firm or Individual Name		William R. Reid		PATENT TRADEMARK OFFICE		
Address		Basell USA Inc.				
Address		912 Appleton Road				
City		Elkton		State	MD	ZIP 21921
Country		US		Telephone	410-996-1783	Fax 410-996-1560
ENCLOSED APPLICATION PARTS (check all that apply)						
<input checked="" type="checkbox"/> Specification		Number of Pages 6		<input type="checkbox"/> CD(s), Number		
<input type="checkbox"/> Drawing(s)		Number of Sheets		<input type="checkbox"/> Other (specify)		
<input type="checkbox"/> Application Data Sheet		See 37 CFR 1.76				
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT						
<input type="checkbox"/> Applicant claims small entity status. See 37 CFR 1.27.						FILING FEE AMOUNT (\$)
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees						
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number:		08-2336		\$160.00		
<input type="checkbox"/> Payment by credit card. Form PTO-2038 is attached.						
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.						
<input checked="" type="checkbox"/> No.						
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are: _____						

Respectfully submitted,

Date 08/27/2003

SIGNATURE

William R. Reid

TYPED or PRINTED NAME

William R. Reid

TELEPHONE

410-996-1783

REGISTRATION NO.

47,894

(if appropriate)

Docket Number:

FE 6122 (US)

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

EXPRESS MAILING CERTIFICATE


This certifies that the attached Form PTO/SB/16 (in duplicate), Specification (6 pages) for the provisional application of Reinhard Kühl et al., for **PROCESS FOR GRANULATING POWDERS OF THERMOPLASTIC POLYMERS** (our ref: FE 6122 (US)) is being mailed by "Express Mail Post Office to Addressee" service in an envelope addressed:

Mail Stop Provisional Patent Application
Commissioner for Patents
P. O. Box 1450
Alexandria, VA 22313-1450

and deposited on **August 27, 2003** as "Express Mail" in the United States Postal Service, the number of the "Express Mail" mailing label being **ER132926898US**.

Douglas Jumps

Typed Name of Person Mailing Paper or Fee



Signature of Person

PROCESS FOR GRANULATING POWDERS OF THERMOPLASTIC POLYMERS

The present invention relates to a process for granulating powders of thermoplastic polymers, in particular thermoplastic polyolefins, preferably ones having a multimodal molar mass distribution, in which the polymer powder prepared in the polymerization reactor or reactors is
5 melted and homogenized in an extruder, then extruded through an extrusion die and subsequently comminuted and cooled.

The granulation of thermoplastic polymers is known and serves to homogenize the polymer and incorporate any auxiliaries and additives such as stabilizers, colorants, agents for improving the mechanical properties, fillers and the like into the polymer. In addition, the
10 handling of thermoplastic polymers during transport and further processing can be improved considerably by granulation compared to the handling of powders.

Apart from the direct coupling of polymerization and granulation, in which the polymer powder from the polymerization process is dried and then fed directly to the extruder, the introduction of polymer powders into the extruder at a temperature corresponding to ambient
15 temperature is customary, particularly in compounding processes. This is due, in particular, to intermediate storage of the polymer powder in silos and the transport methods employing pneumatic conveying systems, where cooling of the powder to ambient temperature can generally occur.

Thus, in compounding, polymer powder is generally fed to the extruder as bulk material at
20 ambient temperature. After the feed zone, the powder has to be increasingly heated in the extruder by mechanical frictional forces and finally melted bit by bit. However, the known granulation processes are still in need of improvement in respect of their throughput, the associated stressing of machines and the product quality of the granulated material.

It is an object of the present invention to provide a process for granulating thermoplastic
25 polymers, in which the effectiveness of the homogenization during granulation is increased at a given throughput or in which the stress on the machines can be reduced, which would be reflected in a reduced energy consumption and a reduced need for repairs or reduced downtimes, or in which the product throughput of existing granulation plants can be increased while maintaining the quality of homogenization.

30 This object is achieved by a process of the generic type mentioned at the outset, in which

an organic solvent or suspension medium is added to the polymer powder in an amount in the range from 0.001 to 20% by weight, based on the weight of polymer powder plus solvent or suspension medium, prior to introduction into the extruder.

5 The addition of solvent or suspension medium according to the invention is preferably effected by the polymer powder, which is prepared in suspension in the polymerization reactor, not being subjected to complete drying but being dried only to such an extent that the desired amount of solvent or suspension medium is automatically established in the polymer powder. The preferred amount of solvent or suspension medium is, according to the invention, in the range from 0.0015 to 15% by weight, particularly preferably from 0.002 to 10% by weight and very
10 particularly preferably from 0.01 to 5% by weight.

A further possible way of achieving the object using the invention is to take a previously dried polymer powder, mix this powder with an appropriate amount of organic solvent or suspension medium and then feed the mixture to the extruder for granulation.

15 According to the invention, organic solvent or suspension media used are saturated or alicyclic or polycyclic or aromatic hydrocarbons having from 3 to 18, preferably from 4 to 12, carbon atoms or a mixture thereof.

As a result of the presence of the amount according to the invention of solvent or suspension medium, the enthalpy of fusion of the polymer powder is reduced and the homogenization in the extruder is improved at a given energy input, which is reflected in fewer
20 specks being observed in the polymer.

Advantageous polymers which can be granulated particularly well by the process of the invention have been found to be, in particular, standard polymers such as polyolefins, polyesters or polyamides, preferably polyethylene or polypropylene. In the case of polyethylene, the process of the invention is particularly useful when the polyethylene has a multimodal molar mass
25 distribution, because additional swelling effects then occur in the case of this material and these lead to particularly favorable homogenization.

The process of the invention has, in particular, the advantage that the granulation can be carried out industrially under improved economic conditions. The costs of drying polymer powders are significantly reduced because the particularly energy-intensive and costly drying step
30 for removing the last 5% of suspension medium can be dispensed with. The product quality is

improved since fewer specks occur and the polymer is thermally and mechanically stressed to a lesser extent in the extruder. The machine running times for the extruders are increased because less energy is required for a given throughput of polymer powder and the material present is thus subjected to lower stresses and thus requires fewer repairs. Conversely, the throughput is increased when the machines are operated at the same energy input, which improves the profitability of the process.

Example 1 (according to the invention)

A bimodal polyethylene was prepared in suspension in hexane as suspension medium in the presence of a high-activity Ziegler catalyst in two reaction vessels connected in series. The bimodal polyethylene had a proportion of 48% by weight of low molecular weight homopolymer and a proportion of 52% by weight of high molecular weight copolymer. The density of the bimodal polyethylene was 0.955 g/cm³, while its MFI₅ was 0.35 dg/min.

The pulverulent polyethylene was subjected to the normal drying process after leaving the reaction vessel, but the process was stopped at an early stage so that precisely 2.2% by weight of hexane remained in the polymer powder.

The powder was introduced into an extruder and processed at a constant energy input to produce granules. Films having a thickness of 25 µm were subsequently produced from the granules in a blown film process, and these were examined for the presence of specks by visual examination under a microscope. The result is shown in the following table.

Example 2 (comparative example)

The same polymer as in Example 1 was subjected to the normal drying process after leaving the reaction vessel, but the process was continued to completion, so that less than 0.001% by weight of hexane remained in the polymer powder.

The powder which had been dried in this way was introduced into the same extruder as in Example 1 and processed to produce granules under exactly the same conditions. Films having a thickness of 25 µm were produced from the granules on the blown film plant and these were subjected to the same examination as in Example 1.

Table	
	Number of specks
Example 1	396/100 cm ²
Example 2	1408/100 cm ²

Claims

1. A process for granulating powders of thermoplastic polymers, in which the polymer powder prepared in a polymerization reactor is melted and homogenized in an extruder, then extruded through an extrusion die and granulated, wherein an organic solvent or suspension medium is added to the polymer powder in an amount in the range from 0.001 to 20% by weight, based on the total weight of polymer powder plus solvent or suspension medium, prior to introduction into the extruder.
2. The process as claimed in claim 1, wherein the thermoplastic polymers used are polyolefins.
3. The process as claimed in claim 1 or 2, wherein the polymers used are polyolefins having a multimodal molar mass distribution.
4. The process as claimed in any of claims 1 to 3, wherein the addition of solvent or suspension medium is effected by the polymer powder, which is prepared in suspension in the polymerization reactor, not being subjected to complete drying but being partly dried only to such an extent that the desired amount of solvent or suspension medium is established in the range from 0.001 to 20% by weight in the polymer powder.
5. The process as claimed in any of claims 1 to 3, wherein the addition of solvent or suspension medium is effected by addition to dry polymer powder so that the desired amount of solvent or suspension medium is established in the range from 0.001 to 20% by weight in the polymer powder.
6. The process as claimed in any of claims 1 to 3, wherein the addition of solvent or suspension medium is effected by introduction into the extruder so that the desired amount of solvent or suspension medium is established in the range from 0.001 to 20% by weight in the polymer powder.
7. The process as claimed in any of claims 1 to 6, wherein the amount of solvent or suspension medium in the powder of thermoplastic polymer is in the range from 0.0015 to 15% by weight.
8. The process as claimed in any of claims 1 to 7, wherein the amount of solvent or suspension medium in the powder of thermoplastic polymer is in the range from 0.002 to 10% by weight.

9. The process as claimed in any of claims 1 to 8, wherein the amount of solvent or suspension medium in the powder of thermoplastic polymer is in the range from 0.01 to 5% by weight.
10. The process as claimed in any of claims 1 to 9, wherein the organic solvent or suspension medium used is a saturated or cyclic or polycyclic or aromatic hydrocarbon having from 3 to 18, preferably from 4 to 12, carbon atoms.

Abstract

In a process for granulating thermoplastic polymers, in particular thermoplastic polyolefins, the polymer powder prepared in the polymerization reactor is melted and homogenized in an extruder, then extruded through an extrusion die and granulated. According to the invention, an organic solvent or suspension medium is added to the polymer powder in an amount in the range from 0.001 to 20% by weight, prior to introduction into the extruder. The invention is particularly useful for granulating polyethylene or polypropylene.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.